


description

performance

Characteristics	Standards	Units	
Description			Safety and anti-slip vinyl
General performance	BS EN ISO 10874: 2012	Class	2.00 : 34 / 43
	BS EN 649 : 2011	Group	P
Usage			Medium to heavy foot traffic
Special treatment			Easy maintenance
Overall thickness	EN 428	mm	2.00
Thickness of wear layer	EN 429, ASTM F410	mm	2.00
Weight	EN 430	g/m ²	2.00 mm : 3500
Sheet size	EN 426	m (width)	2
		m (length)	15 / 20
		m ² (surface area)	30 / 40
Abrasion resistance	EN 660 -2	Group	P
	EN 660 -2	Volume loss mm ³	< 4
	ASTM D3389 (Weight loss / 1000 cycles)	g	< 0.40
Residual indentation	EN 433	mm	- 0.04 (≤ 0.10)
	ASTM F970 (static load)	psi	800
	ASTM F1914	inches	Avg. 0.001
Slip resistance	DIN 51130		R 12
	BS 7976-2 (pendulum method)		Low slip potential
	EN 13893	Coefficient of friction	DS (> 0.30)
	ASTM D2047		Pass (0.70 avg)
Dimensional stability	EN 434	%	≤ 0.40
Flexibility	EN 435	mm	< 20
	ASTM F137		Pass
Castor chair test	EN 425	Type of use	Continuous
Sound insulation	EN ISO 717-2	Δ Lw = dB	4
Reaction to fire	EN ISO 9239-1: 2010	kW/m ²	≥ 8
	EN ISO 11925-2: 2010		Pass
	EN 13501-1:2007+A1: 2009	Class	Bfl - S1
	ASTM E648-06	Type	1
Static electrical propensity	EN 1815	kV	< 2.0
Electrical resistance	EN 1081	Ω	10 ¹⁰
Thermal resistance	ISO 8302 (EN 12664)	k/W m ²	< 0.00568
	ASTM 1514		Pass
Smoke density	ASTM E 662-05	Dm	< 450
Colour fastness to light	EN ISO 105 - B02	Degrees	≥ 6
Walking resonance	NF XPS 31 074		NA
Stain & chemical resistance	BS EN ISO 26987: 2012	Index	0 (Excellent resistance)
	ASTM F925		Pass
Fungi & bacteria resistance	(E1) PCP	%	NA
	ASTM G - 21		Does not favour growth
	ASTM D3273		Pass
Clean rooms	ASTM F51/68	Class	NA
Maritime usage	IMO RES A 653 (16)		Annex 1 part 2 (Smoke & Toxicity)
	IMO MSC 61 (67)		Part 5 (Spread of Flame) and Annexure 2
	US Coast Guard approved		(Surface Flammability / Heat Release)
	Marine Equipment Directive		1121 

*NA - Not applicable