

## **410 Airug**<sup>®</sup> Construction of microcellular vinyl with ribbed pattern



### Ergonomic, Anti-fatigue & Safety Matting - Dry Areas Linear Lengths 410 Airug<sup>®</sup>

Basic worker comfort derived from 9.4 mm thick worker platform comprised of a construction of microcellular vinyl consisting of millions of air bubbles.

- Ribbed pattern enhances traction
- All four sides are bevelled and sealed to minimize tripping hazards
- Slip resistance R10 according to DIN51130 and BGrule BGR181

### Recommended use

- Dry Areas
- For placement in manufacturing plants, assembly lines, picking, packing and logistics warehouses, individual work stations.
- Light duty

### Colors:

- Black
- Black/Yellow .
- Grey

### Sizes:

- 60cm x 91cm •
- 90cm x 150cm .
- 122cm x linm
- 60cm x linm .
- 91cm x linm •
- 122cm x 18.3m
- 60cm x 18.3m .
- 91cm x 18.3m





WEAR RESISTANCE

SLIP RESISTANCE

ANTI-FATIGUE



# Ergonomic, Anti-fatigue & Safety Matting - Dry Areas Linear Lengths $Airug^{\ensuremath{\texttt{B}}}$

### General

Brand	Notrax
Category	Dry Areas Linear Lengths
Product Number	410
Product Family	Industrial & Commercial Matting
Product Group	Ergonomic, Anti-fatigue & Safety Matting
Product Name	Airug®
Recommended use	For placement in manufacturing plants, assembly lines, picking, packing and logistics warehouses, individual work stations.
Shipping Location	Achterzeedijk 57, Unit 15, Barendrecht 2992SB, The Netherlands, Moselle, MS 39459, United States
Туре	Dry Areas - Comfort™
Update trigger	20210310-1301
Usage Intensity	Light duty

## Sustainability

REACH	Reach compliant (Registration, Evaluation, Authorization and Restriction of Chemicals).
Rohs US	Rohs compliant (Restriction of Hazardous Substances).
Sustainability	Recyclable material
Warranty	1

### Tests

Abrasion Resistance 1000	22.0%
Abrasion Resistance 500	12.6%
Compression Deflection 1.4	0.58 cm
Compression Deflection 2.8	0.63 cm
Elongation	160.6%
Fire rating EU	Class 2 according NFPS Safety Code 101
Fire rating US	Pass
Hardness	20 Shore A
Slip Rating	R10
Coefficient Friction Dry	0.78
Surface Flammability	Pass
Tear Strength	6.5 lb



## **Technical Specifications**

Application	Industrial Environments
Breaking Load	29.1 lb
Edges	Bevelled edges on all sides
Material	Microcellular vinyl
Material Group	Vinyl
Process	Foaming

B2 Athy Business Campus, Athy, Co. Kildare, R14 PK74 01 5312777 sales@pittman.ie



1310 Solihull Parkway, Birmingham Business Park, Birmingham, B37 7YB 0121 630 3527 sales@pittman.uk

IE: 015312777 | sales@pittman.ie | www.pittman.ie

UK: 0121 630 3527 | sales@pittman.uk | www.pittman.uk